

DOP 1020-113370 (AB) 1020-117934(VL)

Fabrieksmethode Mode de fabrication Herstellungsverfahren Manufacturing process	Getuft, 5/16" lussenpool Tufté, 5/16" velours bouclé Getuftet, 5/16" Schlinge Tufted, 5/16" loop pile	
Samenstelling van de pool Composition du velours Nutzschicht Pile composition	100 % zuivere scheerwol 100 % laine vierge 100 % reine Schurwolle 100 % pure new wool	
Tuftdoek Support Trägergewebe Primary backing	100 % PP	
Rug Dossier Rücken Secondary backing	Actionback	Vlies Feutre Vliesrücken Fleece
Poolhoogte Hauteur du velours Polhöhe Pile height	7 mm	7 mm
Totale hoogte Hauteur totale Gesamthöhe Total height	10 mm	12 mm
Aantal noppen Nombre de points Noppenzahl Tuft density	34 000/m ²	34 000/m ²
Poolgewicht Poids du velours Polgewicht Pile weight	1 000 g/m ²	1 000 g/m ²
Totaal gewicht Poids total Gesamtgewicht Total weight	2 065 g/m ²	2 385 g/m ²
Warmte isolatie Résistance à la conductibilité de chaleur Wärmedurchlasswiderstand Resistance of heat conduction	ISO 8302	0,17 m ² K/W (theoretisch) Tog Rating 1.7
Gebruik Utilisation Verwendungsbereich Suitability	Huishoudelijk : normaal gebruik Résidentiel : usage normal Wohnen : mittlere Beanspruchung Domestic : medium duty	

Bij verlijming : enkel gebruik van lijmen zonder hoogkokende oplosmiddelen ! / En cas de pose collée : seulement utilisation des colles écologiques !
Bei geklebter Verlegung : nur hochsiederefreie Klebstoffe verwenden ! / In case of adhesion : only use of ecological glues !

We reserve the right to modify the characteristics of this product for quality improvement.

