

DOP 1020/130583 (A) – DOP 1020/130652 (F)

Fabrieksmethode	Getuft, 1/10" lussenpool met structuur, getwijd garen.		
Mode de fabrication	Tufté, 1/10" velours bouclé structuré, fil retord.		
Herstellungsverfahren	Getuftet, 1/10" Schlinge hoch-tief, gezwirte garne.		
Manufacturing process	Tufted, 1/10" structured loop pile, multiplied yarn.		
Samenstelling van de pool	100 % zuivere scheerwol		
Composition du velours	100 % laine vierge		
Nutzschicht	100 % reine Schurwolle		
Pile composition	100 % pure new wool		
Tuftdoek			
Support	100 % PP		
Trägergewebe			
Primary backing			
Rug	Actionback	1	5
Dossier	Feltbacking	4 + 5 m	4 + 5 m
Rücken		Snow	Linnen
Secondary backing			
Poolhoogte		10	35
Hauteur du velours		4 + 5 m	4 + 5 m
Polhöhe	4.5 mm	Beige	Silver Grey
Pile height			
Totale hoogte	6.5 mm (A)	40	45
Hauteur totale	7,5 mm (F)	4 + 5 m	4 + 5 m
Gesamthöhe		Mid Grey	Eclipse
Total height			
Aantal noppen			
Nombre de points			
Noppenzahl	145.700/m²		
Tuft density			
Poolgewicht			
Poids du velours			
Polgewicht	800 g/m²		
Pile weight			
Totaal gewicht	1950 g/m² (A)		
Poids total	2150g/m² (F)		
Gesamtgewicht			
Total weight			
Warmte isolatie	ISO 8302		
Résistance à la conductibilité de chaleur	0,14 m² K/W (theoretisch) (A)/ Tog rating 1.4 (A)		
Wärmedurchlasswiderstand	0,16 m² K/W (theoretisch) (F)/ Tog rating 1.6 (F)		
Resistance of heat conduction	0,16 m² K/W (theoretisch)		
Gebruik	Huishoudelijk : normaal gebruik		
Utilisation	Usage d'habitation normale		
Verwendungsbereich	Wohnen : mittlere Beanspruchung		
Suitability	Domestic : medium duty		

Bij verlaging : enkel gebruik van EC1-lijmen ! / En cas de pose collée : seulement utilisation des colles EC1 !

Bei geklebter Verlegung : nur EC1-Klebstoffe verwenden ! / In case of adhesion : only use of EC1 glues !

We reserve the right to modify the characteristics of this product for quality improvement.



